

# A Review on Zinc Oxide Nanoparticles and Their Applications

Renu Bala<sup>1</sup>, Ashutosh Dixit<sup>1</sup>, Bhawna Pareek<sup>1</sup>, Avnish Kumar Arora<sup>2</sup>, Ashun Chaudhary<sup>3\*</sup>,  
Vivek Sheel Jaswal<sup>4\*</sup>

<sup>1</sup>Department of Chemistry, M.M.E.C., M. M. (Deemed to be University), Mullana, Ambala (Haryana), India - 133207

E-mail: [renusheoran031@gmail.com](mailto:renusheoran031@gmail.com)

<sup>2</sup>Department of Chemistry, Vardhaman College, Bijnor (U.P.), India - 246701

<sup>3</sup>Department of Plant Science (Botany), Temporary Academic Block Shahpur, Central University of Himachal Pradesh, Dharamshala, H.P

<sup>4</sup>Department of Chemistry, S.M.D.R.S.D. College, Pathankot (Punjab) 145001

Running Title: ZnO Nanoparticle

\*Corresponding Authors: Dr Vivek Sheel Jaswal, Department of Chemistry, S.M.D.R.S.D. College, Pathankot (Punjab) 145001

Dr Ashun Chaudhary, Department of Plant Science (Botany), Temporary Academic Block Shahpur, Central University of Himachal Pradesh, Dharamshala, H.P

E-mails: [chemsheel@gmail.com](mailto:chemsheel@gmail.com) , [ashun.chaudhary@gmail.com](mailto:ashun.chaudhary@gmail.com)

Key Words: ZnO nanoparticle, method, characterization, applications

## ABSTRACT

Nanotechnology allocate with the production and usage of material with nanoscale dimension, nanoparticles are large surface area to volume ratio and thus very specific properties. Zinc oxide (ZnO) nanoparticles had been in current studies due to its large bandwidth and high exciton binding energy and it has prospective applications such as Antimicrobial activity, Antioxidant activity · Cytotoxic activity, Photocatalytic degradation's magnetic and chemical properties that are significantly different from those of bulk counterpart. The aims of this review to provide a comprehensive view on structural, synthesis and electrochemical properties of the ZnO nanoparticles, which were synthesized by different methods.

## INTRODUCTION

Nanomaterials call “a wonderful technology”. It controlled to crystalline nanomaterials (less than 100nm), can demonstrate atomic habits owing to their broad surface area that results from greater surface energy and a wider range of valence and conductive range split into nuclear dimensions [1]. A green chemical method for the synthesis of metal and metallic oxide NPs was intended to decrease the toxicity of the environment. The application of dangerous toxic products in physicochemical synthesis subsequently appeared to be toxic and environmentally non-biodegradable [2]. NPs have been built into different manufacturing, food, chemical, storage and other industries that require the strategy of its synthesis to be green and environmentally friendly [3]. Due to multiple interesting and special characteristics, NPs are synthesized worldwide. ZnO is regarded as one of the finest metal oxides in all metal oxides. Due to its distinctive optical and electric characteristics, it can be used on a nanoscale [4,5]. It is one of the toughest material and widely used in health product formulation. Different chemical techniques for synthesizing ZnO NPs have been suggested, i.e. vapour transport, process of rainfall, Zinc response, etc. [6]. ZnO has huge applications in different fields among the metal oxides NPs e.g. the sensing of optical, gas and magnetic [7], their exclusive catalytic, magnetic and electronic properties have been widely researched and have been studied [8]. ZnO is a widely recognized n-type semiconductor with band gap (3.37eV) and has strong binding energies (60 meV) [9-10]. For the smaller Nano sized particles, Zn- ion accumulation is high, where Zn from ZnO micro particles were exposed to less [11-12]. For the biosynthesis of ZnO NPs Zinc acetate [13-15] and Zinc nitrate [16-18] are two mainly investigated substrates. Green NPs synthesis with plant extracts is becoming increasingly important in chemical synthesis. Plant extract acts as bio template plants for nanoparticle synthesis. The techniques are mostly used for synthesis of metal nanoparticle are chemical precipitation [19-20], hydrothermal [21-23], sol-gel [24] and electrochemical and photochemical reduction [25-,26]. One of the primary applications of ZnO NPs is their use as an efficient drug delivery system [27-28]. Several studies have recently used ZnO NPs as a drug delivery

mechanism in multiple diseases. It has been shown that this nanoparticle can target certain drugs to different cells and tissues. In the packaging of foodstuffs, ZnO NPs have been used and several matrices and techniques have been reported for integrating ZnO in these matrices and are included in the packaging system, without interference with the food-protective effects [29]. Nanoparticles biosynthesis is a method used for the synthesis of biomedical nanoparticles applications. This is a competitive, healthy, environmentally friendly and renewable solution [30]. Green synthesis includes fungal, algae and bacterial synthesis. These synthesized NPs demonstrate increased catalytic activity and restrict the application of costly and toxic chemicals.

TABLE

S. NO	METAL	SIZE	SHAPE	METHODS	CHARACTERIZATION	APPLICATION	REFERENCE
1	ZN	0.452 $\mu$ m	Rod - shape	Green synthesis	EDX, XRD, FTIR, SEM	Antibacterial activity	Nurul Izwanie Rasli Et al (2020) <sup>31</sup>
2	ZN	15 to 50 nm	Spherical shape	Green synthesis	FTIR, XRD, SEM, and TEM, UV-Visible spectroscopy	Antibacterial Activity	Basheer Ahmed Fahimmunisha et al (2020) <sup>32</sup>
3	ZN	30.34 nm	Spherical shape	Green synthesis	UV, FTIR, PSA, XRD, XPS, and TEM	anti-biofilm activity	K. Saravana kumar et al (2020) <sup>33</sup>
4	ZN	32-40 nm	Spherical shape	Bio-synthesized	SEM with EDAX, TEM, UV-Vis, FTIR, PL	Antimicrobial activity, anti-cancer activity, Photocatalytic Degradation	M.Nilavukkarasi et al (2020) <sup>34</sup>
5	ZN	5 to 18 nm	Spherical shape	Green synthesis	FTIR, TEM SEM, XRD	antibacterial activity	A.M. Awwad et al (2020) <sup>35</sup>
6	ZN	40 nm	Spherical shape	Green synthesis	UV- Visible spectroscopy EDX, XRD, FTIR, SEM	antibacterial activity, anticancer activity	K.Shreema et al (2020) <sup>36</sup>
7	ZN	52-70 nm	Spherical shape	Green synthesis	FTIR, SEM, TEM, UV-Visible spectroscopy	antifungal activity	Hilal Ahmad Et al (2020) <sup>37</sup>
8	ZN	40 and 50 nm	Hexagonal shape	Biosynthesized	PXRD, EDX, TEM, UV-Visible spectroscopy FESEM	antifungal activity	Abdolhossien Miri et al (2020) <sup>38</sup>
9	ZN	36 nm	Rod shape	Biosynthesis	UV- Visible spectroscopy, XRD, TEM	Antimicrobial activity	Dina E.El-Ghwas et al (2020) <sup>39</sup>
10	ZN	35 and 129 nm	round-shaped	Green synthesis	UV- Visible spectroscopy, FTIR, XRD and AFM	Antifungal activity	Teles Souza JM et al (2019) <sup>40</sup>
11	ZN	60-80 nm	Spherical shape	Green synthesis	UV- Visible spectroscopy XRD, SEM and EDAX, FTIR	Antibacterial Activity	Agarwal Happy et al (2019) <sup>41</sup>

					spectroscopy.		
12	ZN	50 nm	Spherical shape	Green synthesis	SEM, TEM, FTIR, XRD, UV- Visible spectroscopy	Antimicrobial activity	Cui-Ping Gong et al (2019) <sup>42</sup>
13	ZN	20 – 40 nm	Spherical shape	Green synthesis	FTIR, TEM FESEM, XRD	Anti-angiogenesis; anti-inflammatory	Ghasem Rahimi Kalateh Shah Mohammed et al (2019) <sup>43</sup>
14	ZN	30-57 nm	Hexagonal shape	Green synthesis	FESEM, EDX, XRD, UV- Visible spectroscopy	antibacteriaactivity	Raja Adibah Raja Ahmad Et al (2019) <sup>44</sup>
15	ZN	50.6 to 61.7 nm	Spherical shape	microwave-assisted	FESEM, FTIR, XRD	antibacteriaactivity	Nurul amira Ahmad Yusof et al (2019) <sup>45</sup>
16	ZN	80.1 to 90 nm	rod-like shaped	Sonochemicalmethod	TEM, XRD, FTIR, SEM	Antibacteriaactivity	Roberta C et al (2019) <sup>46</sup>
17	ZN	12.63 nm	Spherical shape	Green synthesis	XRD, TEM, SEM	antibacterial activity, anticancer activity	S.Shahid et al (2019) <sup>47</sup>
18	ZN	24 nm	Spherical shape hexagonal shaped	Green synthesis	UV- Visible spectroscopy FTIR, XRD SEM,EDAX, TEM	Biocompatibility anti-inflammatory	H. Agarwal et al (2019) <sup>48</sup>
19	ZN	25 nm	Spherical shape	Green synthesis	FTIR, XRD, SEM, TEM, UV- Visible spectroscopy	Antimicrobial activity, Antioxidant	Ashraf Ahmadi Shadmehris et al (2019) <sup>49</sup>
20	ZN	66.25 nm	Irregular Spherical shape	Biosynthesis	FTIR, XRD, SEM, TEM, UV- Visible Spectroscopy	Antimicrobial activity, Antioxidant, cytotoxic activity	Huzaifa Umar et al (2019) <sup>50</sup>
21	ZN	20-130 nm	Rod shaped	Green synthesis	XRD, FE-SEM, EDX, FTIR	Antibacterial agents Antioxidant activity · cytotoxic activity	Devaraj Bharathi et al (2019) <sup>51</sup>
22	ZN	20 nm	Spherical shape	Green synthesis	UV- Visible spectroscopy SEM,TEM, FTIR, XRD,	Antimicrobial activity	D. Wang et al (2018) <sup>52</sup>
23	ZN	50 to 500 nm	Pseudo spherical	Green synthesis	UV- Visible spectroscopy, XRD, TEM FTIR	Antimicrobial activity	Manjari barsainya et al (2018) <sup>53</sup>
24	ZN	10 to 90 nm	rectangular shape	Green synthesis	UV- Visible spectroscopy	Antimicrobial activity,	Mehrdad Khatami et al

					XRD,XPS, SPR, FESEM, EDAXSS		(2018) <sup>54</sup>
25	ZN	2 to 10 nm	Spherical shape	Green synthesis	UV- Visible spectroscopy, TEM, SEM, XRD, FTIR	Antibacterial Activity	Syed Md Humayun Akhter et al (2018) <sup>55</sup>

**Nurullzwani Rasli (2020) et al** synthesized ZnO-NPs using Aloe vera plant extract by green process. The total number of particles (18-618)  $\mu\text{m}$  with a rod-shaped outline was also demonstrated to be Antibacterial activity. **Basheer Ahmed Fahimmunisha (2020) et al** synthesized ZnO-NPs with Aloe sococritine leaf extract by green process. The scale of nanoparticles is spherically shaped between 15-50 nm and shows Antibacterial activity of ZnO nanoparticles. **Kandasamy Saravana kumar (2019) et al** reported T-ZnO and T- $\beta$ -D-Glu-ZnO NPs with medium size spherical shape 30.34 nm and in vivo analysis of their antibody. There has been examination of Antibacterial activity. **M. Nilavukkarasi (2019) et al** synthesized ZnO-NPs with the spherical form ranging from 32-40 nm by the green process. ZnO nanoparticles demonstrates Antimicrobial, Anticancer and Methylene blue photodegradation. **Akl M. Awwad (2020) et al** synthesized the average ZnO-NPs produced were 5-18 nm using aqueous fruit plant extracts by green process. ZnO-NPs are a spherically efficient antibacterial agent and are considered a possible addition to toxic chemicals. **k. Shreema (2020) et al** measured ZnO-NPs at around 40 nm of spherical form. Zinc oxides may also be able to predict the potential for anticancer activity against human osteosarcoma cell line (MG63). The green synthesis of ZnO-NPs is also recorded through the green process using Evolvulusalesinoids leaf extract. **Hilal Ahmed (2020) et al** synthesizing ZnO-NPs by a green method of spherical shapes with dimensions from 52-70 nm and also showing the Antifungal activity. **Abdolhossien Miri (2020) et al** synthesized ZnO-NPs using the Prosopisfarcta fruit extract by green method, hexagonalizing ZnO-NPs ranging from 40-50 nm. The Cytotoxic and Antifungal activity was demonstrated. **Dina E.El Ghwa (2020) et al** synthesized ZnO-NPs by green methods. Nanoparticles with rod type ranged in diameter from 11.6-43.97 nm and exhibit antimicrobial activity. **Jessica Maria Teles Souza (2019) et al** synthesized ZnO-NPS by a green process. The size of nanoparticles varies from 35-129 nm and is spherical in shape. Antifungal activity against parapsilosis is demonstrated by the synthesized nanoparticles. **Agarwal Happy (2019) et al** synthesized ZnO-NPs using Cassia alata plant extract by green process also reported the average size of the synthesized NPs is 60-80 nm and spherical in shape. This study has also demonstrated the excellent antibacterial potential of ZnO-NPs through growth curvature analysis and bactericidal nanoparticles activity. **Cui-Ping Gong (2019) et al** synthesized green model ZnO-NPs with an average size of 50 nm and a spherical shape. Efficient production of biofilm against bacterial pathogens was developed. **Ghasem Rahimi Shammed (2019) et al** synthesized ZnO-NPs with the extract of Hyssops Officialis. The synthesized nanoparticles demonstrate Anti-inflammatory agents and Anti-angiogenesis activity with an average spherical shape size with 20-40 nm. **Nuru Amira Ahmad Yusof (2019) et al** synthesized ZnO-NPs with the help of partially-microwave heat have been successful. ZnO nanoparticles were distributed uniformly in 50.6-61.7 nm range, with spherical shapes. Nanoparticles of chitosan/ ZnO have been shown to be inhibited by bacteria. **Robert C. Desouza (2018) et al** synthesized ZnO-NPs from the ZnO process. Rod-like particles range from 80.1-90 nm. Strong antibacterial activity was observed with the Sonochemical ZnO-Nps. **S. Sahid (2019) et al** synthesized ZnO-NPs with Eucalyptus globules leaf extract using a green process. The spherical form of the NPs is 12.63 nm. Cytotoxic and Antioxidant substances have also been identified. **Happy Agarwal (2019) et al** synthesized ZnO-NPs using Pinnate leaf extract of the average crystalline size 24 nm with a spherical shape. It has been also shows Antiviral activity. **Ashraf ahmadi Shadmehar (2019) et al** synthesizes ZnO-NPs by biosynthesis process which is evenly distributed over the surface of the grapheme without aggregation. Antibacterial and Antioxidant activity is seen in medium size of 25 nm and spherical types. **Huzaifa Umar (2019) et al.** synthesized ZnO nanoparticles with a spherical size range of 66.25nm in diameter with antimicrobial and antioxidant activity. **Devraj Bharathi (2018) et al** synthesized ZnO-NPs with 20-130 nm rod formation. Synthesized nanoparticles with good Antibacterial activity against positive gram and negative gram bacteria are assisted by biophlavonoid rutin. **Dongyan Wang (2019) et al** synthesized ZnO-NPs which was effective through a safe, easy and green path. The TEM picture showed the spherical form with 20 nm diameter. Gram-positive and Gram-negative Anti-microbial effects were studied for ZnO-NPs and the discodification technique was used to examine yeast. **Manjari Barsainya (2018) et al** synthesizes nanoparticles with extract of Pseudomonas aeruginosa. The TEM images of ZnO-NPs display pseudo-sphere morphology with a particle size range of 20-100 nm. The function of the Antimicrobial is also demonstrated. **Mehrdad Khatami (2018) et al** synthesized ZnO NPs with green synthesis, the synthesized nanoparticles of rectangular shape ranging from 10-90nm. The antimicrobial applications of zinc oxide nanostructure are demonstrated. **Syed Md Humayun Akhter (2018) et al.** synthesized ZnO NPs by Swertia chirayit leaf extract. TEM micrographs reveal that the particles are nearly spherical. The antibacterial effects of gram-negative ZnO NPs are in the range of 2-10nm.

## Conclusions

Due to its several characteristics, ZnO NPs provides incredible opportunities in potential applications of Antimicrobial, photocatalytic, antifungal, antibacterial, anticancer Encouraging advancement in researching ZnO NPs has been accomplished and discussed in this paper. An additional significant natural and synthetic methods have been introduced for large- scale applications to attain a wide range of programmable structures for the construction of reconfigurable architectures.

## REFERENCE

- [1]. Van Dijken, A., Meulenkaamp, E. A., Vanmaekelbergh, D., & Meijerink, A. (2000). Identification of the transition responsible for the visible emission in ZnO using quantum size effects. *Journal of Luminescence*, 90(3-4), 123-128.
- [2]. Andersson, M., Pedersen, J. S., & Palmqvist, A. E. (2005). Silver nanoparticle formation in microemulsions acting both as template and reducing agent. *Langmuir*, 21(24), 11387-11396.
- [3]. Rao, M. D., & Gautam, P. (2016). Synthesis and characterization of ZnO nanoflowers using *C. hlamydomonas reinhardtii*: A green approach. *Environmental Progress & Sustainable Energy*, 35(4), 1020-1026.
- [4]. Vayssieres, L., Keis, K., Hagfeldt, A., & Lindquist, S. E. (2001). Three-dimensional array of highly oriented crystalline ZnO microtubes. *Chemistry of Materials*, 13(12), 4395-4398.
- [5]. Könenkamp, R., Dloczik, L., Ernst, K., & Olesch, C. (2002). Nano-structures for solar cells with extremely thin absorbers. *Physica E: Low-Dimensional Systems and Nanostructures*, 14(1-2), 219-223.
- [6]. Sabir, S., Arshad, M., & Chaudhari, S. K. (2014). Zinc oxide nanoparticles for revolutionizing agriculture: synthesis and applications. *The Scientific World Journal*, 2014.
- [7]. Sosa, I. O., Noguez, C., & Barrera, R. G. (2003). Optical properties of metal nanoparticles with arbitrary shapes. *The Journal of Physical Chemistry B*, 107(26), 6269-6275.
- [8]. Sun, Y., Mayers, B., Herricks, T., & Xia, Y. (2003). Polyol synthesis of uniform silver nanowires: a plausible growth mechanism and the supporting evidence. *Nano letters*, 3(7), 955-960.
- [9]. Alivov, Y. I., Kalinina, E. V., Cherenkov, A. E., Look, D. C., Ataev, B. M., Omaev, A. K., ... & Bagnall, D. M. (2003). Fabrication and characterization of n-ZnO/p-AlGaIn heterojunction light-emitting diodes on 6H-SiC substrates. *Applied Physics Letters*, 83(23), 4719-4721.
- [10]. Calestani, D., Zha, M., Mosca, R., Zappettini, A., Carotta, M. C., Di Natale, V., & Zanotti, L. (2010). Growth of ZnO tetrapods for nanostructure-based gas sensors. *Sensors and Actuators B: Chemical*, 144(2), 472-478.
- [11]. Gulson, B., Wong, H., Korsch, M., Gomez, L., Casey, P., McCall, M., ... & Greenoak, G. (2012). Comparison of dermal absorption of zinc from different sunscreen formulations and differing UV exposure based on stable isotope tracing. *Science of the total environment*, 420, 313-318.
- [12]. Holmes, A. M., Song, Z., Moghimi, H. R., & Roberts, M. S. (2016). Relative penetration of zinc oxide and zinc ions into human skin after application of different zinc oxide formulations. *ACS nano*, 10(2), 1810-1819.
- [13]. Davar, F., Majedi, A., & Mirzaei, A. (2015). Green synthesis of ZnO nanoparticles and its application in the degradation of some dyes. *Journal of the American Ceramic Society*, 98(6), 1739-1746.
- [14]. Hassan, S. S., El Azab, W. I., Ali, H. R., & Mansour, M. S. (2015). Green synthesis and characterization of ZnO nanoparticles for photocatalytic degradation of anthracene. *Advances in Natural Sciences: Nanoscience and Nanotechnology*, 6(4), 045012.
- [15]. Fatimah, I., Pradita, R. Y., & Nurfalinda, A. (2016). Plant extract mediated of ZnO nanoparticles by using ethanol extract of *Mimosa pudica* leaves and coffee powder. *Procedia engineering*, 148, 43-48.
- [16]. Diallo, A., Ngom, B. D., Park, E., & Maaza, M. (2015). Green synthesis of ZnO nanoparticles by *Aspalathus linearis*: structural & optical properties. *Journal of Alloys and Compounds*, 646, 425-430.
- [17]. Sutradhar, P., & Saha, M. (2016). Green synthesis of zinc oxide nanoparticles using tomato (*Lycopersicon esculentum*) extract and its photovoltaic application. *Journal of Experimental Nanoscience*, 11(5), 314-327.

- [18]. Thema, F. T., Manikandan, E., Dhlamini, M. S., & Maaza, M. (2015). Green synthesis of ZnO nanoparticles via *Agathosma betulina* natural extract. *Materials Letters*, 161, 124-127.
- [19]. Zhong, Q., & Matijević, E. (1996). Preparation of uniform zinc oxide colloids by controlled double-jet precipitation. *Journal of Materials Chemistry*, 6(3), 443-447.
- [20]. W. Lingna, M. Mamoun, J. Mater. Chem. 9 (1999) 2871
- [21]. Hui, Z., Deren, Y., Xiangyang, M., Yujie, J., Jin, X., & Duanlin, Q. (2004). Synthesis of ZnO nanoparticles by hydrothermal method. *Nanotechnology*, 15, 622-629.
- [22]. Sun, L., Yin, J., Su, H., Liao, C., & Yan, C. (2002). Control of ZnO morphology via a simple solution route. *Chem Mater*, 14(10), 4172-4177.
- [23]. Li, W. J., Shi, E. W., Zheng, Y. Q., & Yin, Z. W. (2001). Hydrothermal preparation of nanometer ZnO powders. *Journal of materials science letters*, 20(15), 1381-1383.
- [24]. Bahnemann, D. W., Kormann, C., & Hoffmann, M. R. (1987). Preparation and characterization of quantum size zinc oxide: a detailed spectroscopic study. *Journal of physical chemistry*, 91(14), 3789-3798.
- [25]. Chen, W., Cai, W., Zhang, L., Wang, G., & Zhang, L. (2001). Sonochemical processes and formation of gold nanoparticles within pores of mesoporous silica. *Journal of colloid and interface science*, 238(2), 291-295.
- [26]. A. Frattini, N. Pellegrini, D. Nicastro, O.D. Sanctis, Matter. Chem. Phys. 94 (2005) 14.
- [27]. Taylor, E., & Webster, T. J. (2011). Reducing infections through nanotechnology and nanoparticles. *International journal of nanomedicine*, 6, 1463.
- [28]. Asharani, P. V., Wu, Y. L., Gong, Z., & Valiyaveetil, S. (2008). Toxicity of silver nanoparticles in zebrafish models. *Nanotechnology*, 19(25), 255102.
- [29]. Espitia, P. J. P., Soares, N. D. F. F., dos Reis Coimbra, J. S., de Andrade, N. J., Cruz, R. S., & Medeiros, E. A. A. (2012). Zinc oxide nanoparticles: synthesis, antimicrobial activity and food packaging applications. *Food and bioprocess technology*, 5(5), 1447-1464.
- [30]. Yu, L., Liu, S., Yang, B., Wei, J., Lei, M., & Fan, X. (2015). Sn–Ga co-doped ZnO nanobelts fabricated by thermal evaporation and application to ethanol gas sensors. *Materials Letters*, 141, 79-82.
- [31]. Rasli, N. I., Basri, H., & Harun, Z. (2020). Zinc oxide from aloe vera extract: two-level factorial screening of biosynthesis parameters. *Heliyon*, 6(1), e03156.
- [32]. Fahimmunisha, B. A., Ishwarya, R., AlSalhi, M. S., Devanesan, S., Govindarajan, M., & Vaseeharan, B. (2020). Green fabrication, characterization and antibacterial potential of zinc oxide nanoparticles using *Aloe socotrina* leaf extract: A novel drug delivery approach. *Journal of Drug Delivery Science and Technology*, 55, 101465.
- [33]. Saravanakumar, K., Jeevithan, E., Hu, X., Chelliah, R., Oh, D. H., & Wang, M. H. (2020). Enhanced anti-lung carcinoma and anti-biofilm activity of fungal molecules mediated biogenic zinc oxide nanoparticles conjugated with  $\beta$ -D-glucan from barley. *Journal of Photochemistry and Photobiology B: Biology*, 203, 111728
- [34]. M. Nilavukkarasi, S. Vijayakumar, S. Prathipkumar, *Capparis zeylanica* mediated biosynthesized ZnO nanoparticles as antimicrobial, photocatalytic and anti-cancer applications, *Materials Science for Energy Technologies* (2020), doi: <https://doi.org/10.1016/j.mset.2019.12.004>
- [35]. Awwad, A. M., Amer, M. W., Salem, N. M., & Abdeen, A. O. (2020). Green synthesis of zinc oxide nanoparticles (ZnO-NPs) using *Ailanthus altissima* fruit extracts and antibacterial activity. *Chemistry International*, 6(3), 151-159.
- [36]. Shreema, K., Kalaiselvi, V., & Mathammal, R. (2020). Green Synthesis and Characterization of Zinc Oxide Nanoparticles Using Leaf Extract of *Evolvulus Alsinoides*. *Studies in Indian Place Names*, 40(18), 763-778.
- [37]. Ahmad, H., Venugopal, K., Rajagopal, K., De Britto, S., Nandini, B., Pushpalatha, H. G., ... & Jogaiah, S. (2020). Green Synthesis and Characterization of Zinc Oxide Nanoparticles Using *Eucalyptus globules* and Their Fungicidal Ability Against Pathogenic Fungi of Apple Orchards. *Biomolecules*, 10(3), 425.
- [38]. Abdolhossien Miri, Mehrdad Khatami, Omolbanin Ebrahimi & Mina Sarani (2020) Cytotoxic and antifungal studies of biosynthesized zinc oxide nanoparticles using extract of *Prosopisfarcta* fruit, *Green Chemistry Letters and Reviews*, 13:1, 27-33, DOI:10.1080/17518253.2020.1717005

- [39]. El-Ghwas, D. E., Mazed, T. E., El-Waseif, A., Al-Zahrani, H. A., Almaghrabi, O. A., & Elazzazy, A. M. (2020). Factorial Experimental Design for Optimization of Zinc Oxide Nanoparticles Production. *Current Nanoscience*, 16(1), 51-61.
- [40]. Teles Souza JM, Rodrigues de Araújo A, Aguiar de Carvalho AM, Amorim AdrianydasGraçNascimento, Daboit TC, Roberto de Souza de Almeida Leite José, Alves da Silva D, Eaton P, sustainably produced cashew gum-capped zinc oxide nanoparticles show antifungal activity against *Candida parapsilosis*, *Journal of Cleaner Production* (2019), doi: <https://doi.org/10.1016/j.jclepro.2019.119085>.
- [41]. Happy, A., Soumya, M., Kumar, S. V., Rajeshkumar, S., Sheba, R. D., Lakshmi, T., & Nallaswamy, V. D. (2019). Phyto-assisted synthesis of zinc oxide nanoparticles using *Cassia alata* and its antibacterial activity against *Escherichia coli*. *Biochemistry and biophysics reports*, 17, 208-211.
- [42]. Gong, C. P., Luo, Y., & Pan, Y. Y. (2019). Novel synthesized zinc oxide nanoparticles loaded alginate-chitosan biofilm to enhanced wound site activity and anti-septic abilities for the management of complicated abdominal wound dehiscence. *Journal of Photochemistry and Photobiology B: Biology*, 192, 124-130.
- [43]. Mohammad, G. R. K. S., Tabrizi, M. H., Ardalan, T., Yadamani, S., & Safavi, E. (2019). Green synthesis of zinc oxide nanoparticles and evaluation of anti-angiogenesis, anti-inflammatory and cytotoxicity properties. *Journal of biosciences*, 44(2), 30.
- [44]. Ahmad, R. A. R., Harun, Z., Othman, M. H. D., Basri, H., Yunus, M. Z., Ahmad, A., ... & Ainuddin, A. R. (2019). Biosynthesis of zinc oxide nanoparticles by using fruits extracts of *Ananas comosus* and its antibacterial activity. *Malaysian Journal of Fundamental and Applied Sciences*, 15(2), 268-273.
- [45]. Yusof, N. A. A., Zain, N. M., & Pauzi, N. (2019). Synthesis of Chitosan/Zinc Oxide Nanoparticles Stabilized by Chitosan via Microwave Heating. *Bulletin of Chemical Reaction Engineering & Catalysis*, 14(2), 450-458.
- [46]. Souza, R. C. D., Haberbeck, L. U., Riella, H. G., Ribeiro, D. H., & Carciofi, B. A. (2019). Antibacterial activity of zinc oxide nanoparticles synthesized by solochemical process. *Brazilian Journal of Chemical Engineering*, 36(2), 885-893.
- [47]. Shahid, S., Fatima, U., Sajjad, R., & Khan, S. A. (2019). Bioinspired Nanotheranostic Agent: Zinc Oxide; Green Synthesis and Biomedical Potential. *Dig J. Nanomater. Biostruct*, 14, 1023-1031.
- [48]. Agarwal, H., & Shanmugam, V. K. (2019). Synthesis and optimization of zinc oxide nanoparticles using *Kalanchoe pinnata* towards the evaluation of its anti-inflammatory activity. *Journal of Drug Delivery Science and Technology*, 54, 101291.
- [49]. Ahmadi Shadmehri, A., Namvar, F., Miri, H., Yaghmaei, P., & Nakhaei Moghaddam, M. (2019). Assessment of antioxidant and antibacterial activities of Zinc Oxide nanoparticles, Graphene and Graphene decorated by Zinc Oxide nanoparticles. *International Journal of Nano Dimension*, 10(4), 350-358.
- [50]. Umar, H., Kavaz, D., & Rizaner, N. (2019). Biosynthesis of zinc oxide nanoparticles using *Albizia lebbek* stem bark, and evaluation of its antimicrobial, antioxidant, and cytotoxic activities on human breast cancer cell lines. *International journal of nanomedicine*, 14, 87.
- [51]. Bharathi, D., & Bhuvaneshwari, V. (2019). Synthesis of zinc oxide nanoparticles (ZnO NPs) using pure bioflavonoid rutin and their biomedical applications: antibacterial, antioxidant and cytotoxic activities. *Research on Chemical Intermediates*, 45(4), 2065-2078.
- [52]. Wang, L. Cui, X. Chang, et al., Biosynthesis and characterization of zinc oxide nanoparticles from *Artemisia annua* and investigate their effect on proliferation, osteogenic differentiation and mineralization in human osteoblastlike MG-63 Cells, *Journal of Photochemistry & Photobiology, B: Biology*(2018), <https://doi.org/10.1016/j.jphotobiol.2019.111652>
- [53]. Barsainya, M., & Singh, D. P. (2018). Green Synthesis of Zinc Oxide Nanoparticles by *Pseudomonas aeruginosa* and their Broad-Spectrum Antimicrobial Effects. *J Pure Appl Microbiol*, 12(4), 2123-2134.
- [54]. Khatami, M., Alijani, H. Q., Heli, H., & Sharifi, I. (2018). Rectangular shaped zinc oxide nanoparticles: Green synthesis by *Stevia* and its biomedical efficiency. *Ceramics International*, 44(13), 15596-15602.s

[55] Akhter, S. M. H., Mahmood, Z., Ahmad, S., & Mohammad, F. (2018). Plant-mediated green synthesis of zinc oxide nanoparticles using *Swertia chirayita* leaf extract, characterization and its antibacterial efficacy against some common pathogenic bacteria. *BioNanoScience*, 8(3), 811-817.

